

Ghent, 01/09/2011

MATERIAL SAFETY DATA SHEET

Rubber composition of SOLIDEAL BLACK tyres / tracks:

ELASTOMER (NR, SBR, BR)	60 %
CARBON BLACK + OTHER FILLERS	35 %-32 %
PROCESSING AGENTS	1-2 %
CURING AGENTS	2 %-3 %
PROTECTING AGENTS	2 %-3 %

Furthermore our compounds are NITROSAMINE FREE and contain LOW-PAH oil, in line with the Directive 2005/69/CE and REACH, annex XVII, both from the EU.

Thierry MICHE
Senior Manager Technical Service, Warranty & Systems

CS-ETC N.V. is the Authorised Engineering Company for all SOLIDEAL products.